

# Barricade<sup>®</sup> Dry Step<sup>™</sup>

## Technical Data

### PRODUCT SPECIFICATIONS

A high quality reinforcing polypropylene scrim with a unique top Antislip surface laminated to specialty film using a proprietary resin blend.

WEIGHT	140 g/m <sup>2</sup> ± 5 % (4.1 oz/yd <sup>2</sup> ± 5%) finished weight
LENGTH OF ROLL	76 m (250')
WIDTH OF ROLL	1.2 m (48")
WEIGHT OF ROLL	13.2 kg (29 lbs)
COLOR	GRAY

### TENSILE STRENGTH ASTM D751-95

Machine Direction	Force	154 lbs.	70 kg.
	Elongation		
Cross Direction	Force	110 lbs.	50 kg.
	Elongation		

### TRAPEZOIDAL TEAR STRENGTH ASTM D4533-91

Machine Direction	Force	40 lbs.	18 kg.
Cross Direction	Force	35 lbs.	16 kg.

### UV ACCELERATED WEATHERING ASTM G154-98

More than 90% Strength retained after 2,000 hours\* Exposure

Mullen Burst ASTM D751-95	220 psi	1517 kPa
Nominal Thickness	14 mils	0.35mm

Note: all values are +/- 10%

\* QUV A-340 lamps 8hrs UV @60°C, 4hrs Condensation @40°C

The test data is based on an average taken over several production runs and should not be considered or interpreted as minimum or maximum values. Values are typical data and not limiting specifications.